

IN THE UNITED STATES PATENT AND TRADEMARK OFFICE

UNITED STATES PATENT APPLICATION

APPARATUS FOR HYDROENHANCING FABRICS  
USING A SHAPED ORIFICE

INVENTORS:

Herschel Sternlieb  
21 McKeen Street  
Brunswick, Maine 04011

Paul F. Zolin  
1 Huntington Common Drive No. 106  
Kennebunk, Maine 04043

APPLICANTS' PATENT AGENT

Charles Frederick Seyboldt  
Registration No. 41,304

19 Ridgeview Drive  
Standish, Maine 04084

(207) 893-0352

**APPARATUS FOR HYDROENHANCING FABRICS  
USING A SHAPED ORIFICE**

**CROSS REFERENCE TO RELATED APPLICATIONS**

5

This application is a divisional of application  
Ser. No. 09/902,050, filed July 10, 2001.

**BACKGROUND OF THE PRESENT INVENTION**

10

**SUMMARY OF THE PRIOR ART**

15

20

25

This invention relates to a **method for hydroenhancing fabrics**, and more particularly to a **method for hydroenhancing fabrics using a shaped orifice** wherein a liquid under pressure is forced through a non-circular orifice in a coherent jet and impinges onto a fabric. Multiple orifices are typically used, and the shape and orientation of the orifices (e.g. the distance between adjacent orifices, the angle between the major axes of the orifices and the direction of fabric travel and the direction of impingement) can be modified to effect different hydroenhancement properties. The method of hydroenhancement can be practiced using a variety of machinery configurations. One use for the method of the present invention is to impart "striping," i.e. a

selective color wash-out to produce a pattern of alternating lighter and darker stripes across the width, and running the length of a fabric web..

5           The impingement of a liquid under pressure onto a fabric (hydroenhancement) to modify the properties of fabric materials is well known.

10           U.S Patent **3,560,326**, Australian Patent **287,821** and Canadian Patent **739,652** to **J. Bunting**, U.S. Patents **4,957,456** and **5,737,813** to **Sternlieb**, U.S. Patents **5,791,028** and **6,253,429** to **Zolin**, and various other disclosures describe the use of pressurized liquid, usually water, exiting a manifold through an arrangement  
15           of circular orifices arranged either in a single line or in a pattern on an orifice strip; either impinging on a bat of loose fibers to make a non-woven fabric, or impinging on a fabric to change its properties.

20           U.S. Patent **4,152,480** to **Adachi**, U.S. Patent **4,085,486** to **Brandon**, and U.S. Patent **3,906,130** to **Tsurumi** disclose the use of a single slot having a length that is equal to or greater than the width of the web of cloth being treated. In these references, the slot is

arranged so as to cover the entire width of a cloth web,  
and the pressure of the liquid is limited due to the  
bending and deformation of the slot opening induced by  
the force of liquid pressure operating over a long  
5. unsupported length. This technology is useful for hydro-  
entanglement, i.e. the process of making a fabric from a  
loose bat of non-interwoven loose fibers, but the energy  
available at the maximum pressure is not adequate to  
appreciably alter the appearance or properties of a pre-  
10 existing fabric.

U.S. Patent **4,960,630** to **Greenway** describes the use  
of a fan "jet" array. A fan "jet" has an elongated  
opening, usually appearing as a sector of a circle, that  
15 produces a fan-shaped spray. In the fan-shaped spray,  
the liquid emerges from the opening in various  
directions, i.e. the fan-shaped spray is not columnar or  
coherent.

20 European Patent Application **0,177,277** of **Wilbanks,**  
**et al** discloses a method of imparting a pattern onto  
fabric using jets of water that are emitted in "pulses."  
This process is much less efficient, time wise, than the  
method of the present invention.

The method disclosed in U.S. Patent **5,737,813** to **Sternlieb** could be used to create a stripe pattern, but because the energy delivered by a single circular orifice is insufficient to provide adequate wash-out, the  
5 striping effect must be produced either with a series of orifices in multiple manifolds, or by making multiple passes through one machine.

It is not feasible to simply increase the number of  
10 orifices per inch in order to deliver more energy per pass. The material that comprises an orifice strip must be of sufficient thickness to withstand the liquid pressure behind it. This thickness is usually about ten time greater than the diameter of a typical circular  
15 orifice, e.g. an orifice strip having .003 inch diameter (or wide) orifices can be from about .010 up to .040 inch thick. If the orifice passage was a constant .003 inch diameter (or width) for the full .040 inch of its length, the resulting stream would become divergent, i.e. would  
20 not be coherent or columnar. In order to produce coherent or columnar jet that retains its effectiveness over greater distances, an orifice passage can be relieved at the exit end. This construction reduces the effective length of the orifice passage and results in a

coherent or columnar jet. A negative side effect of this construction is to create a minimum distance between adjacent orifices, in order to retain adequate material in, and strength of, the orifice strip.

5

It is difficult to make and maintain multiple orifice/manifolds alignment so that successive impingements fall on the same wash-out line; with the result that the striping becomes blurred. Similarly, multiple pass striping operation requires precise repeatability of fabric tracking, and also an absence of shrinkage in the width direction of the fabric throughout the time required to make the required number of passes. If the tracking deviates or width shrinkage occurs, the striping becomes blurred.

10

15

The above references describe a variety of fabric support means. Fabric support is variously described as being flat or curved, smooth or textured, non-porous or foraminous; with certain combinations of the properties being used in any given application (e.g. a curved, smooth and foraminous roll; or a flat and textured conveyor "screen;" or a flat smooth and non-porous conveyor belt). Foraminous surfaces are described as

20

being made of mesh screen material, or being a perforated sleeve. Another variable involves whether the fabric support is stationary, i.e. whether the fabric is "dragged" over the support (typically referred to as an "impact box"); or is moving with, or even effecting the transport of, the fabric.

In the fabric support configurations that involve a foraminous support, the references also disclose the use of a vacuum to enhance the hydroenhancement process. The vacuum keeps the water from pooling or flooding, and thereby impeding the ability of the water jets to impinge the fabric. The vacuum can also facilitate the handling of the fabric by holding it tight to the support or support/transport member.

The above references also describe a variety of fabric transport means. Fabric transport can involve the use of a flat conveyor, or a serpentine path through a series of rolls. Additionally, the methods and apparatus of the prior art range from single-pass operations, using multiple manifolds and jet arrays; to multi-pass operations; to reciprocating operations where the fabric web travels first in one direction, then in the reverse

direction, and possibly repeats this forward/reverse cycle numerous times in order to achieve a desired degree of hydroenhancement.

5           Further, the above references describe a variety of impingement angles, that is the angle at which a coherent jet strikes the surface of the fabric. In some cases the impingement is perpendicular to the fabric surface, but in other cases it is deliberately not.

10           The above references also describe methods of hydroenhancement where only one, or both sides of a fabric are subjected to the liquid jet impingement.

15           In the Detailed Description of the Preferred Embodiment of U.S. Patent **6,253,429** to **Zolin**, at column 7, rows 9-12, is the statement that ". . . other diameter orifices and other orifice shapes can also be employed." However, nothing in the references shows or suggests an  
20           elongated orifice shape, or an orifice other than a circle.



## SUMMARY OF THE PRESENT INVENTION

The present invention contemplates hydroenhancing fabrics with a liquid exiting a pressurized manifold through an array of elongated orifices. The liquid jet emanating from each elongated orifice is columnar or coherent in form, i.e. its cross section has minimum variation from where the liquid jet exits the orifice to where the liquid jet impinges the fabric. The benefits of using elongated orifices are several: to permit the presence of solid impurities in the pressurized liquid that would clog an array of circular orifices; to improve the energy efficiency of the hydroenhancement process; to reduce the number of passes required to create the desired hydroenhancement effect; to simplify the "striping" of fabrics, i.e. making a consistent pattern of alternating lighter and darker lines across the width of the fabric web with a single manifold and orifice strip; to permit hydroenhancing of high-warp-count fabrics without undesirable patterning; and to simplify the machinery that would be required to accomplish any given degree of hydroenhancement.

The range of methods and apparatus that can embody

the present invention are as varied as the prior art. That is, fabric support can be flat or curved, smooth or textured, non-porous or foraminous; and fabric transport can likewise be provided in many varieties.

5

The distinguishing characteristic of the present invention over the prior art is the use of elongated orifices. One elongated orifice that is .003 inch wide and .030 inch long can deliver approximately ten times as much energy as a circular orifice of .003 inch diameter. This property permits the development of hydroenhancing machines with fewer manifolds and orifice strips, resulting in less expensive equipment, and/or quicker processing times for the hydroenhancement of a fabric.

15

The method of hydroenhancing fabrics of the present invention comprises forcing liquid water under pressure out of a manifold through an orifice strip having a number of openings that are generally rectangular in shape. By using an orifice strip with elongated orifices, it is possible to achieve novel and reproducible striping effects at high production speeds.

20

The method according to the present invention can

also be used to hydroenhance non-woven fabrics; provided the non-woven bats are in a cohesive condition or state.

The present invention relates to a **method for**  
5 **hydroenhancing fabrics using a shaped orifice** that may be adapted and adjusted to optimize the hydroenhancement process, and further may be adapted to produce a variety of patterns in fabrics by varying the size, number and/or orientation of the shaped orifices. Specific features of  
10 the invention will be apparent from the above and from the following description of the illustrative embodiments when considered with the attached drawings and the appended claims.

15 In **summary**, and in accordance with the above discussion, the foregoing **objectives** are achieved in the following embodiments.

20 1. A method for hydroenhancing a fabric comprising the steps of:

(a) providing a support surface for the fabric;

(b) providing a supply of pressurized liquid;

(c) providing a manifold having a longitudinal axis and having at least one opening for the discharge of the pressurized liquid, where the opening has a length dimension that is at least one and a half times its width and the longitudinal axis of the opening is not parallel to the longitudinal axis of the manifold, where the pressurized liquid emerges from the opening as a jet;

(d) directing the liquid jet toward the support surface;

(e) interposing the fabric between the support surface and the manifold; and

(f) inducing relative motion between the fabric and the manifold.

2. The method of hydroenhancing a fabric as described in **paragraph 1** where the manifold has multiple openings for the discharge of the pressurized liquid.

3. The method of hydroenhancing a fabric as described in **paragraph 2** where the direction of relative

motion between the fabric and the manifold is perpendicular to the longitudinal axis of the manifold.

4. The method of hydroenhancing a fabric as  
5 described in **paragraph 2** where the liquid jets are directed toward the support surface in a direction that is normal to the support surface.

5. The method of hydroenhancing a fabric as  
10 described in **paragraph 2** where the liquid jets are directed toward the support surface at an angle that is at least 5 degrees from normal to the support surface.

6. The method of hydroenhancing a fabric as  
15 described in **paragraph 2** where the support surface is flat.

7. The method of hydroenhancing a fabric as  
20 described in **paragraph 2** where the support surface is curved.

8. The method of hydroenhancing a fabric as described in **paragraph 1** where the longitudinal axis of the opening is perpendicular to the longitudinal axis of

the manifold.

5        9. The method of hydroenhancing a fabric as described in **paragraph 1** where the longitudinal axis of the opening is at a non-perpendicular angle to the longitudinal axis of the manifold.

10       10. The method of hydroenhancing a fabric as described in **paragraph 2** where the longitudinal axes of the openings are parallel and the distances between adjacent openings are equal.

15       11. The method of hydroenhancing a fabric as described in **paragraph 2** where the longitudinal axes of the openings are parallel and the distances between adjacent openings are varied.

20       12. The method of hydroenhancing a fabric as described in **paragraph 1** where

the opening has a liquid-entry face and a liquid-exit face and has side walls defined by elements connecting the liquid-entry and liquid-exit faces; and

the elements of the side walls are parallel so that the liquid-entry face and liquid-exit face have substantially the same size and shape.

5           **13.** The method of hydroenhancing a fabric as described in **paragraph 1** where

the opening has a liquid-entry face and a liquid-exit face and has side walls defined by elements  
10, connecting the liquid-entry and liquid-exit faces; and

the elements of the side walls are divergent running from the liquid-entry face toward the liquid-exit face so that the liquid-exit face is substantially larger than  
15 the liquid-entry face.

**14.** The method of hydroenhancing a fabric as described in **paragraph 10** where the openings have a width from about two one-thousandths of an inch to about ten  
20 one-thousandths of an inch (.002-.010 inch) and a length of at least twice their width.

**15.** The method of hydroenhancing a fabric as described in **paragraph 14** where the longitudinal axes of

the openings are perpendicular to the longitudinal axis of the manifold.

5        **16.** The method of hydroenhancing a fabric as described in **paragraph 14** where the longitudinal axes of the openings are not perpendicular to the longitudinal axis of the manifold.

10       **17.** The method of hydroenhancing a fabric as described in **paragraph 10** where:

15       the openings have a width from about two one-thousandths of an inch to about ten one-thousandths of an inch (.002-.010 inch) and a length of at twice their width; and

      each of the openings has about the same width and length.

20       **18.** The method of hydroenhancing a fabric as described in **paragraph 10** where:

      the openings have a width from about two one-thousandths of an inch to about ten one-thousandths of an



inch (.002-.010 inch) and a length of at least twice their width;

each of the openings is about the same width; and

5

the openings have varying lengths.

19. The method of hydroenhancing a fabric as described in **paragraph 11** where the openings have a width from about two one-thousandths of an inch to about ten one-thousandths of an inch (.002-.010 inch) and a length of at least twice their width.

10

20. The method of hydroenhancing a fabric as described in **paragraph 19** where the longitudinal axes of the openings are perpendicular to the longitudinal axis of the manifold.

15

21. The method of hydroenhancing a fabric as described in **paragraph 19** where the longitudinal axes of the openings are not perpendicular to the longitudinal axis of the manifold.

20

22. The method of hydroenhancing a fabric as

described in **paragraph 11** where:

the openings have a width from about two one-  
thousandths of an inch to about ten one-thousandths of an  
5 inch (.002-.010 inch) and a length of at least twice  
their width; and

each of the openings has about the same width and  
length.

10

**23.** The method of hydroenhancing a fabric as  
described in **paragraph 11** where:

the openings have a width from about two one-  
15 thousandths of an inch to about ten one-thousandths of an  
inch (.002-.010 inch) and a length of at least twice  
their width;

each of the openings has about the same width; and

20

the openings have varying lengths.

**24.** The method of hydroenhancing a fabric as  
described in **paragraph 2**, where the support surface is

foraminous.

25. The method of hydroenhancing a fabric as described in **paragraph 24**, where the support surface has  
5 a first side for supporting the fabric and a second side;  
and

further comprising the step of providing a partial vacuum on the second side of the support surface.

10 26. The method of hydroenhancing a fabric as described in **paragraph 2**, where the fabric is moved past a stationary manifold.

27. Apparatus for hydroenhancing a fabric  
15 comprising:

a support surface for the fabric;

a supply of pressurized liquid;

20 a manifold having a longitudinal axis and having at least one orifice for the discharge of the pressurized liquid, where the orifice

a) has a major axis that is at least one and a half times its minor axis

b) and the major axis of the orifice is not parallel to the longitudinal axis of the manifold

c) and the pressurized liquid emerges from the orifice as a jet directed toward the support surface; and

means for inducing relative motion between the fabric and the manifold.

**28.** The apparatus for hydroenhancing a fabric as described in **paragraph 27** where the manifold has multiple orifices for the discharge of pressurized liquid.

**29.** The apparatus for hydroenhancing a fabric as described in **paragraph 28** where the direction of relative motion between the fabric and the manifold is perpendicular to the longitudinal axis of the manifold.

**30.** The apparatus for hydroenhancing a fabric as

described in **paragraph 28**, where the fabric moves past a stationary manifold.

5       **31.** The apparatus for hydroenhancing a fabric as described in **paragraph 30**, where the support surface is curved.

10       **32.** The apparatus for hydroenhancing a fabric as described in **paragraph 31**, where the support surface is foraminous.

15       **33.** The apparatus for hydroenhancing a fabric as described in **paragraph 32**, where the support surface has a first side for supporting the fabric and a second side; and

          further comprising means for creating a partial vacuum on the second side of the support surface.

20       **34.** The method of hydroenhancing a fabric as described in **paragraph 1** where

          the opening has a liquid-entry face and a liquid-exit face and has side walls defined by elements connecting the liquid-entry and liquid-exit faces; and

the elements of the side walls are divergent running from the liquid-exit face toward the liquid-entrance face so that the liquid-entrance face is substantially larger than the liquid-exit face.

5

### BRIEF DESCRIPTION OF THE DRAWINGS

**Figure 1** is a plan view of a moving fabric web and a  
5 partially cut-away manifold.

**Figure 2** is a side elevation view of a moving fabric  
web, a manifold and an orifice strip.

10 **Figure 3** is an elevation view of a fabric web in a  
serpentine path showing circular fabric supports and  
manifolds in two different positions.

**Figure 4** is a depiction of an orifice strip having  
15 equally-spaced, parallel, similar length elongated  
orifices.

**Figure 5** is a depiction of another orifice strip  
having equally-spaced, parallel, similar length elongated  
20 orifices.

**Figure 6** is a depiction of an orifice strip having  
variably spaced, parallel, variable length elongated  
orifices.

**Figure 7** is a depiction of an orifice strip having yet another arrangement of elongated orifices.

**Figure 8** is a depiction of an orifice strip showing  
5 two elongated orifices.

**Figure 9** is a cross-sectional view taken on line **IX-IX** of **Figure 8**.

10 **Figure 10** is a cross-sectional view taken on line **X-X** of **Figure 8**.



**DESCRIPTION OF THE PREFERRED EMBODIMENTS  
OF THE PRESENT INVENTION**

5           **Figure 1** is a plan view of a moving web and a partially cut-away manifold.

          In one embodiment of the present invention, a fabric web **4** passes underneath a manifold **10**. Partially shown  
10       in the cut-away portion of manifold **10** is the orifice strip **30** and a series of parallel elongated orifices **40** in the orifice strip **30**, where the major axes of the elongated orifices **40** are parallel with the direction of travel of fabric web **4**. In **Figure 1**, manifold **10** is  
15       placed so its longitudinal axis is perpendicular to the direction of travel of fabric web **4**, and fabric web **4** appears to be on a flat support surface (not shown). However, it is within the practice of the present invention to orient manifold **10** so that its longitudinal  
20       axis is not perpendicular to the direction of travel of fabric web **4**.

**Figure 2** is a side elevation view of a moving web, a manifold and an orifice strip.

In one embodiment of the present invention, moving fabric web **4** passes underneath manifold **10** and orifice strip **30**. Liquid under pressure is contained in manifold **10**, and exits through orifices in the orifice strip **30**.

5 In the view of **Figure 2**, the direction of impingement of the columnar jet of liquid is normal, or perpendicular to the surface of the fabric. However, it is contemplated that the present invention can also be practiced where the angle of impingement is non-normal to the fabric  
10 surface. Further, **Figure 2** shows the fabric web in a flat orientation. But, the present invention can also be practiced with the fabric web being in a curved configuration.

15 **Figure 3** is an elevation view of a fabric web in a serpentine path showing circular fabric supports and manifolds in three different positions.

Moving fabric web **4** can be threaded through a series  
20 of rolls **20**, **22** with manifolds **10**, **10'**, **10''** arranged so as to direct liquid jets toward the web. In **Figure 3**, rolls **20** are called support rolls because they are associated with a manifold (**10**, **10'**, **10''**). Roll **22** is not a support roll, but could be either an idler roll or

a drive roll. Support rolls **20** can be either smooth or textured, or can be porous or non-porous, and can be produced in a variety of diameters to effect differing amounts of curvature to the moving fabric web **4**.

5

Manifold **10** and orifice strip **30** are arranged so that the columnar jets of liquid impinge the moving fabric web **4** in a near-normal direction. Alternate arrangements are shown by the placement of manifolds **10'** and **10''** and orifice strips **30'** and **30''** so that the columnar jets of liquid impinge the moving fabric web **4** in a non-normal direction. The amount of "offset" can be varied, either by displacing a manifold laterally as is shown by manifold **10'**, or by rotating a manifold about its longitudinal axis as shown by manifold **10''**.

10

15

**Figure 4** is a depiction of an orifice strip having equally-spaced, parallel, similar length elongated orifices.

20

One possible arrangement of elongated orifices in orifice strip **30** is shown in **Figure 4**. Orifice strip **30** has two faces, face **35** being the face where the liquid under pressure will emerge. The major axes of the

elongated orifices according to this embodiment will be perpendicular to the longitudinal axis of the manifold (not shown).

5           An arrangement where the major axes of the elongated orifices are parallel to the direction of fabric web travel is the preferred mode for striping operations, and for most fabric hydroenhancement operations when practicing the present invention. **Figure 6**, below, also  
10       shows an arrangement of elongated orifices where (with the manifold longitudinal axis perpendicular to the fabric travel direction) the major axes of the elongated orifices are parallel to the direction of fabric web travel.

15           **Figure 5** is a depiction of another orifice strip having equally-spaced, parallel, similar length elongated orifices.

20           In the orifice strip **30** of **Figure 5**, the major axes of the elongated orifices will be at an oblique (non-perpendicular) angle to the longitudinal axis of the manifold (not shown). Various angles of inclination can be practiced using the principles of the present

invention, but a practical maximum deviation from perpendicular to the manifold longitudinal axis is about 60 degrees.

5           **Figure 6** is a depiction of a orifice strip having variably spaced, parallel, variable length elongated orifices.

10           In a striping operation, the amount of wash-out varies depending on the amount of energy delivered to the fabric. Elongated orifices of greater length will provide more wash-out than orifices having shorter length. The color of the stripe can be varied by changing the length of the elongated orifice, i.e. a  
15           longer orifice will produce greater color wash-out.

20           By varying the length of the orifices in a pattern as illustrated in **Figure 6**, varying amounts of wash-out occur over the width of the fabric web. Note that the elongated orifices in orifice strip **30** of **Figure 6** are arranged so that there are also varying spaces between adjacent orifices. Where there are no orifices, the fabric is not washed-out, resulting in a more pronounced striping effect. The width of the stripes can be varied

by repeating orifice "clusters" **48**, comprising a certain pattern of orifices, where adjacent orifice clusters **48** are separated by areas having no orifices.

5           The sharpness of the stripe pattern can be varied as well. In the orifice strip **30** of **Figure 6**, orifice cluster **48** is made of individual elongated orifices having the same length. This produces a sharper contrast between washed-out and non-washed-out regions of fabric.  
10 But, the elongated orifices of orifice cluster **48'** have varying lengths. The effect of this is to produce a greater range of wash-out amount. Many different patterns of striping can be produced by varying the number of elongated orifices in an orifice cluster, and  
15 by varying (or not) the length of individual elongated orifices within an orifice cluster.

          An orifice strip of an embodiment shown in **Figure 6** has been shown to produce a seer-sucker effect. This  
20 effect was produced on a light-weight 3.5 ounce sheeting fabric, using elongated orifices about .003 inch wide and .012 in long. The pattern of orifices was three elongated orifices at a pitch 35 per inch then a space equal to three orifices, then three orifices, then a

space, etc.

**Figure 7** is a depiction of a orifice strip having yet other possible arrangements of elongated orifices.

5

The orifice clusters shown in **Figure 7** depict a variety of orifice cluster designs that can be practiced within the present invention. Note that various combinations of length, angle and position are shown, and each of these variables may be used to control the hydroenhancement effect.

10

**Figure 8** is a depiction of an orifice strip showing two elongated orifices.

15

Orifices **42** and **43** are shown from the liquid exit face **35** of orifice strip **30**. Orifice **42** has a constant cross section throughout the thickness of orifice strip **30**, while orifice **43** has a varying cross section, made up of a through hole and relief **44**.

20

**Figure 9** is a cross-sectional view taken on line **IX-IX** of **Figure 8**.

Elongated orifice **42** in orifice strip **30** has a constant cross section throughout the thickness of the orifice strip. Orifice **42** is defined by orifice walls **45**. Walls **45** are a source of friction to the moving liquid as it passes through the orifice **42**. As the liquid emerges from orifice **42** at liquid-exit (or downstream or low pressure) side **35**, the friction is relieved, resulting in the production of a divergent stream of liquid, where the cross section of the stream or jet increases after being emitted from the orifice strip **30**.

**Figure 10** is a cross-sectional view taken on line **X-X** of **Figure 8**.

Elongated orifice in orifice strip **30** can be described as beginning at liquid-entry (or up-stream, or high pressure) side **36**, and progressing toward liquid-exit side **35**. The length of constant cross section defined by walls **45** is less than the thickness of the orifice strip. A relief **44** having angled walls **46** is provided to reduce friction between the rapidly moving liquid and the side walls of the elongated orifice. The result of providing a relief **44** with angled walls **46** is



the production of a columnar stream of liquid, where the cross section of the stream or jet increases very gradually after being emitted from the orifice strip 30.

5           The method of the present invention can be practiced either with elongated orifices similar to orifice 42 of **Figures 8** and **9**, or with relieved elongated orifices similar to orifice 43 and relief 44 as shown in **Figures 8** and **10**. The preferred embodiment uses relieved elongated  
10 orifices.

As shown in **Figures 8** and **10**, and as discussed above, the reliefs 44 are on the low pressure, or liquid exit face of the orifice strip. However, it is possible  
15 to practice the method of the present invention using a relieved orifice where the relief appear on the high pressure or liquid-entrance face of the orifice strip.

#### EXPERIMENTAL RESULTS

20           A test was run using various orifice strips. For all tests: the liquid used was water; the pressure was about 1750 PSIG; and the fabric support surface was a 100 mesh screen having a curved shape. For each test, a

woven 4.7 ounce polyester fabric (44x30/12-10, having a permeability of 1,350 standard cubic feet of air per minute) was subjected to 6 passes at a web velocity of 100 feet per minute, treating alternate sides of the fabric at each pass, i.e. each side of the fabric was treated 3 times.

Orifice Strip A:

circular orifices .003 inch in diameter and spaced 102 orifices per inch.

Orifice Strip B:

circular orifices .005 inch in diameter and spaced 60 orifices per inch.

Orifice Strip C:

circular orifices .007 inch in diameter and spaced 30 orifices per inch.

Orifice Strip D (Present invention):

elongated orifices .003 inch wide by .009 inch long, with the spacing between the orifice major axes being .029 inches (pitch of 35 per inch) and arranged with the major axes of the orifices parallel to the fabric travel

direction and perpendicular to the longitudinal axis of the manifold (elongated orifice arrangement as depicted in **Figure 4**).

5           The chart below summarizes the test parameters. The first column indicates the test subject, the second column indicates the size (in inches) and shape of the test orifices, the third column indicates the area of a single orifice (in square inches) of that size and shape,  
10           the fourth column indicates the "pitch," or number of orifices per inch of length of the jet strip, the fifth column indicates the combined area of the orifices in one inch of test strip (e.g. 102 orifices of .003 inch diameter have a combined area of .007 square inches), and  
15           the sixth column indicates the permeability of the test fabric after the fabric had been hydroenhanced. Air permeability is the number of standard cubic feet of air per minute at a test pressure that will pass through a given area of test fabric. Lower permeability values  
20           indicate a greater degree of hydroenhancement.

Test	Orifice Size	Area per Orifice	Orifice Pitch	Area per inch	Air Perm
A	.003 dia	.000 007	102/inch	.0007	702
B	.005 dia	.000 020	60/inch	.0012	765
C	.007 dia	.000 038	30/inch	.0012	660
D	.003x.009	.000 027	35/inch	.0009	618

The present invention, described above, relates to a  
**method for hydroenhancing fabrics using a shaped orifice.**  
 Features of the present invention are recited in the  
 appended claims. The drawings contained herein  
 necessarily depict structural features and embodiments of  
 the **method for hydroenhancing fabrics using a shaped**  
**orifice**, useful in the practice of the present invention.

However, it will be appreciated by those skilled in  
 the arts pertaining thereto, that the present invention  
 can be practiced in various alternate forms, proportions,  
 and configurations. Further, the previous detailed  
 descriptions of the preferred embodiments of the present

invention are presented for purposes of clarity of understanding only, and no unnecessary limitations should be implied therefrom. Finally, all appropriate mechanical and functional equivalents to the above, which  
5 may be obvious to those skilled in the arts pertaining thereto, are considered to be encompassed within the claims of the present invention.